



TiNOX energy Al

HIGLY SELECTIVE ABSORBER MATERIAL

OPTICAL PROPERTIES

		Typical	Standards
SOLAR ABSORPTION	α_{sol}	95 % \pm 2 %	ASTM E 891-87 and ISO 9845-1
THERMAL EMISSIVITY	$\epsilon_{100^{\circ}\text{C}}$	4 % \pm 2 %	DIN ISO 22975-3
COLOUR ANGLE h		270° < h < 300°	CIE Lab (D65 / 10°)

TECHNICAL DATA

COATING METHOD	PVD	AIR TO AIR COIL COATING
ABSORBER COATING	HIGLY SELECTIVE ABSORBER COATING	ALUMINIUM SUBSTRATE / ADHESION LAYER / CERMET ABSORBER MULTILAYER/ SILICA GLASS ANTI REFLECTION AND PROTECTION LAYER

ENVIRONMENTAL STABILITY

Conditions	Time	PC = $-\Delta\alpha + 0.5\Delta\epsilon$ *	Cross hatch test	Standards
Temperature 291°C	600 h	< 2%	OK	DIN ISO 22975-3
Humidity at 40°C condensing	600 h	< 1%	OK	DIN ISO 22975-3
CLIMATE CHAMBER 85°C – 85% r.H.	1000 h	< 1%	OK	
UV 0,53W/mm ² @ 340nm	100 h	< 1%	OK	

*) Performance criterion "PC" as defined in DIN ISO 22975-3.

MECHANICAL STABILITY

	Value	Standards
CROSS HATCH TEST	No more than 2 of 100 test fields delaminating	ISO 2409 / ASTM D 3359
ADMISSIBLE BENDING RADIUS	\geq 10 mm	



SUBSTRATE: MECHANICAL PROPERTIES

	Value	Standards
ALUMINIUM ALLOY	1050 or purer	EN 573-3
TEMPER	H 18 (hard)	EN 515
TENSILE STRENGTH	≥ 140 N/mm ²	EN 485-2
YIELD STRENGTH 0.2%	≥ 120 N/mm ²	EN 485-2
ELONGATION A ₅₀	> 1 %	EN 485-2
ROUGHNESS:	Ra = 0.2 - 0.5 μm	

SUBSTRATE: PHYSICAL PROPERTIES

	Value	Standards
THERMAL CONDUCTIVITY	> 220 W/mK	
Density	2.71 g/cm ³	

AVAILABLE SIZES

THICKNESS	0.3mm – 0.70mm
WIDTH	≤ 1250mm

TiNOX energy is available also on other metallic substrates as copper or stainless steel on request.

Update 07th February 2024 - Rev. 04

All information provided is based on up-to-date values where possible. Optical values are average results from 0.4mm substrate and are published for guidance only; they may vary according to raw material thickness. For more detailed information please contact our technical sales department. Physical characteristics of the materials are in accordance with EN (European Committee for Standardization).

General tolerance

Gauge tolerance: ± 0.03 mm
 Width tolerance: ± 0.15 mm
 Length-cut sheets: ± 1 mm/m

Note

All materials listed above can be delivered in various sizes and shapes according to customer requirements. Products with protective tape are guaranteed for six months after delivery if they are stored in a conditioned room (temperature 20-30°C and relative humidity 50-60%) and kept away from sunlight and any heating source. Protective tape is not UV resistant.

Almeco S.p.A.
 Via della Liberazione, 15
 20098 San Giuliano Milanese
 (Mi) - Italy
 Tel: +39 02 9889631
 Fax: +39 02 98896399
 E-mail:
info.it@almecogroup.com

Almeco GmbH
 Claude Breda Strasse, 3
 D-06406 Bernburg - Germany
 Tel: +49 3471 3465500
 Fax: +49 3471 3465509
 E-mail:
info.de@almecogroup.com

Almeco USA, INC.
 1610 Spectrum Drive
 Lawrenceville, GA 30043 - USA
 Tel: +1 770 4493454
 Fax: +1 770 4493677
 E-mail: info@almecousa.com

Almeco International Trading Co. Ltd.
 Sales & Marketing: Room A02,
 12F, T2, No 277 Longlan Rd,
 Xu Hui District,
 Shanghai 200232, China
 Tel: +86 21 64755012
 Fax: + 86 21 64755012
 E-mail: info.cn@almecogroup.com